

Datasheet

____ Midnight Blend Waterstruck Facing Brick



| DETA | II C | EBUM | DOD |
|------|------|-------------|-----|

| Brick type / Category | U / 1 | | | | |
|---|--|---|--|-----------|--|
| Intended use | Bricks for use in unprotected masonry | | | | |
| Geometry | G1 | In accordance v | In accordance with EN1996-1-1. | | |
| Dimensions, [mm] | UK-NF | Length 215 | Width 103 | Height 65 | |
| Tolerance, [mm] | T2 | Length ±4 | Width ±3 | Height ±2 | |
| Range, [mm] | Rm | Length 8 | Width 6 | Height 4 | |
| Gross density | 1800 | kg / m ³ | | | |
| Tolerance | D1 | ±10% | | | |
| Compressive strength, average, min | 30 | N/mm ² | | | |
| Compressive strength, normalized, min | 22 | N/mm ² | | | |
| Water absorption, maximum | 11 | Weight% | | | |
| Durability against freeze/thaw | F2 | Freeze/thaw re | esistant | | |
| Active soluble salts content (Category) | S2 | | | | |
| Fire resistance | A1 | contains < 1,0% | contains < 1,0% organic material | | |
| SUPPLEMENTAL INFORMATION | | | | | |
| Initial rate of absorption, average value±tolerance | 1,5 ± 0,4 | kg/m ² | | | |
| Exposure class | MX4 | | | | |
| Bond strength | 0,15 | N/mm ² , table v | N/mm ² , table value, EN 998-2, annex C | | |
| Bricks per m2 with a 12mm mortar joint | 63 | pcs / m ² | pcs / m ² | | |
| Palletising | 80 | pcs | pcs | | |
| Cleaning | Acid-cleaning is not al | Acid-cleaning is not allowed. See instructions for cleaning of masonry at randerstegl.com | | | |
| Mortar selection | The type of mortar is chosen on the basis of characteristics of strength and durability in accordance with static impacts and exposureclass. | | | | |
| Note | Brick is a natural material and variations can thus occur in terms of colour and structure. Therefore please see samples or reference buildings with the brick products in question. | | | | |