

product name			Production location		
Handmade Sundridge Red			Erbaa/Tokat		
Colour					
No description					
Format					
Moulding method Hand form					
DF: 215 x 100 x 65 mm	x 65 mm Between batches t		average size and color may slightly differ.		
Essential Characteristics - EN771-1					
C€		NPD			
Dimensional tolerances		T2			
Range		R1			
Active Soluble Salts		S2			
Mean Compressive strength	>	= 20 N/mm²	Tested to the bed face		
Normalized Compressive strength		NPD	Tested to the bed face		
Dimensional stability		NPD			
Bond Strength general	0,15 N/mm²				
Bond Strength thin layer	C),30 N/mm²			
Reaction to fire	A1		Category		
Water absorption	<=	= 15% m/md			
Water vapour permeability		5/10			
Net dry density	16:	10 kg/m³ (D1)			
Gross dry density	172	20 kg/m³ (D1)			
Thermal conductivity Lambda 50/50	<=	=0,41 W/m.K			
Durability against freeze thaw		F2			
Dangerous substances		NPD	According to Annex ZA 3		
Other Characteristics					
Initial rate of water absorption - Non-coated Bricks	1,5 -	4.0 kg/m².min (IW3)	Value according EN771-1:2011 - 5.3.8		
Initial rate of water absorption - Coated bricks		NPD	Value according EN771-1:2011 - 5.3.8		
Freeze/thaw resistance		NPD	B 27-009		
Thermal conductivity Lambda 90/90		NPD			
Thermal conductivity Lambda Ui		NPD			
Thermal conductivity Lambda Ue		NPD			
	III.				

Storage & handling	Cutting
--------------------	---------

- Store packs on a clean surface and cover them
 Process from multiple packs at the same time
 Follow the Vandersanden processing guidelines

Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).

*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.