

Product Technical Information Sheet

Wienerberger Code 152110

Beerse (Belgium) **Production Plant**

Soft Mud Moulded Stock Manufacture

Configuration Frogged

Colour Red Multi

Appearance Creased

215 x 102.5 x 65 Work Size (mm)

528 No. Pack Quantity

Individual Dry Brick Weight (kg) 2.4

Technical Properties to BS EN 771-1

T1/R1 Size Tolerance (Mean/Range)

Gross Dry Density (kg/m³/Tolerance) 1650 (D1)

Compressive Strength (N/mm²) ≥12

Thermal Conductivity (W/(m·K))

P=90% 0.69 $\lambda_{10,dry,unit}$ value (EN 1745 tabulated: S1)

Durability Designation F2

Water Absorption (%) ≤15

Initial Rate of Water Absorption Min. 1.0 Max. 5.0 $(kg/(m^2 \cdot min))$

Active Soluble Salts S2

Reaction to Fire Class A1

Issue Date: 29/09/2020

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.







1000+ products to choose from



Expert help and advice



Comprehensive Design Services



Technical Support