GRAVEN RED MULTI CBP-ABC-GRAV

Graven Red Multi from the ABC Klinker factory. A sensitive blend of red soft mud facing bricks with a bright & uplifting quality. The handmade texture and colour variations from

The facing bricks are delivered with the following characteristics, in accordance with the CE and Benor marks: NEN-EN 771-1, April 2013, and NEN-EN 771-1/A1, March

Dimensions may vary depending on the production. For the most recent version see www.camtechbp.co.uk. This document is not binding and annuls all previous publications. The manufacturer reserves the right to change the product range and characteristics. The user must always check that they have the most recent descriptive text.

TEXTURE, TYPE & COLOUR Handmade facing bricks for interior and exterior use in

decorative or construction walls.

TECHNICAL CHARACTERISTICS

2005 Category I, HD clay bricks.

<u>NOTE</u>







NEN-EN 771-1, April 2013, and NEN-EN 771-1/A1, March 2005 Category I, HD clay bricks Production Reference code: ABC Klinker Gravenhorst rot-bunt

Length	: 215 mm, T2 (+/- 4 mm), R1 (9 mm)
Width	: 102 mm, T2 (+/- 3 mm), R1 (6 mm)
Thickness	: 65mm, T2 (+/- 2 mm), R1 (5 mm)
Appearance	: Perforated Wirecut, Euro group 1
Average compressive strength	: >35 N/mm2
Dimensional stability	: NPD
Bond strength	: NPD
Active soluble salts	: \$2
Reaction to fire	: Euro class A1
Water absorption	: <6% m/md
Water vapour diffusion coefficient	: 50/100
Gross dry density	: 1600 kg/m3, D1 (10%, +/- 160 kg/m3)
Thermal conductivity	: NPD - EN 1745;2012
Freeze/thaw resistance	: F2



Call Camtech: 01763 262006



We want to help you make informed decisions and find the right solution for your business, customers or project; after all, it's much more than just a product, Right!



CAMTECH BUILDING PRODUCTS LTD p. Camtech House, 21 Jarman Way Royston, Herts, SG8 5HW. UK

t. +44 (0)1763 262006 e. info@camtechbp.co.uk w. camtechbp.co.uk