



Crofters Medley

Product Technical Information Sheet

Wienerberger Code 24170480

Production Plant Denton

Extruded/Wirecut Manufacture

Configuration Perforated

Colour Red Multi

Dragfaced Appearance

215 x 102.5 x 65 Work Size (mm)

400 No. Pack Quantity

2.1 Individual Dry Brick Weight (kg)

Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range) T2/R1

Gross Dry Density (kg/m³/Tolerance) 1480 (D1)

Compressive Strength (N/mm²) ≥40

Thermal Conductivity (W/(m·K))

P=90% 0.69 $\lambda_{\text{10,dry,unit}}$ value (EN 1745 tabulated: S1)

F2 **Durability Designation**

Water Absorption (%) ≤12

Initial Rate of Water Absorption Min. 1.0 Max. 2.2

Active Soluble Salts S2

Reaction to Fire Class A1

Issue Date: 07/09/2020

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to orderina







 $(kg/(m^2 \cdot min))$

1000+ products to choose from



Expert help and advice



Comprehensive Design Services



Technical Support