

BELMONT



Issue Date: January 2021

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102.5 x 65mm
Size Tolerances Mean & Range	T1, R1
Configuration	Perforated
Voids	37%
Mean Compressive Strength	40 N/mm ²
Active Soluble Salts	S2
Water Absorption	6%
Durability	F2
Gross Dry Density	1400 Kg/m ³
Equivalent Thermal Conductivity	0,35 W/mK
Initial Rate of Absorption	0,6 kg/(m ² min)