

Chalfont Blend

size

65mm: 212 x 100 x 65mm 50mm: 212 x 100 x 50mm

compressive strength 35 N/mm²

water absorption ≤ 10%

durability FL / F2 Class 3

weight per pack

65mm: 1390kg, 50mm: 1350kg

pack size

65mm: 632, 50mm: 792

active soluble salts content \$2

dry weight per brick 65mm: 2.2kg, 50mm: 1.8kg

dimensional tolerances T1 Range Category R1





