


## LICHFIELD RED MULTI



[www.brickability.co.uk](http://www.brickability.co.uk)

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: April 2023

## PRODUCT INFORMATION

Packaging	Shrink Wrapped & Banded
-----------	-------------------------

## TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	Tm, Rm
Configuration	Solid
Voids	0%
Mean Compressive Strength	20 N/mm <sup>2</sup>
Active Soluble Salts	S2
Water Absorption	12%
Durability	F2
Gross Dry Density	1740 Kg/m <sup>3</sup>
Equivalent Thermal Conductivity	NPD
Initial Rate of Absorption	NPD